S3110

(UL ANSI: CEM-1)

FEATURES

- Lower warpage
- Good thermal resistance
- Good moisture resistance
- Good mechanical process ability

APPLICATIONS

Display, Power supplier Game machine Keyboard, instrument Household appliances

Test Items	Test Method	Test Condition	Unit	Typical Value
Thermal Stress	IPC-TM-650 2.4.13.1	288℃, solder float	S	>30
Z-axis CTE	IPC-TM-650 2.4.24	50-260 ℃	%	6.2
Permittivity (1MHz)	IPC-TM-650 2.5.5.9	C-24/23/50	-	4.4
Loss Tangent (1MHz)	IPC-TM-650 2.5.5.9	C-24/23/50	-	0.022
Volume Resistivity	IPC-TM-650 2.5.17.1	C-96/35/90	MΩ-cm	7.8×10 ⁸
Surface Resistivity	IPC-TM-650 2.5.17.1	C-96/35/90	ΜΩ	5.6×10 ⁷
Arc Resistance	IPC-TM-650 2.5.1	D-48/50+D-0.5/23	S	118
Dielectric Breakdown	IPC-TM-650 2.5.6	D-48/50+D-0.5/23	kV	>45
Peel Strength (1oz)	IPC-TM-650 2.4.8	288°C/10s	N/mm [lb/in]	1.8 [10.28]
Flexural Strength (LW/CW)	IPC-TM-650 2.4.4	А	Мра	420/358
Water Absorption	IPC-TM-650 2.6.2.1	D-24/23	%	0.13
Flammability	UL94	C-48/23/50	Rating	V-0
СТІ	CTI IEC60112		Rating	PLC 2

GENERAL PROPERTIES

Remarks: 1. Specification sheet: IPC-4101/10, is for your reference only.

2. All the typical value is based on the 1.6mm specimen.

3. All the typical value listed above is for your reference only, please turn to Shengyi Technology Co., Ltd for detailed information, and all rights from this data sheet are reserved by Shengyi Technology Co., Ltd.

PURCHASING INFORMATION

Thickness	Copper foil	Standard size	
0.63mm to 3.2mm	18um to 105 um	915mm ×1,220mm(36"×48") 1,020mm ×1,220mm(40"×48")	
		1,070mm×1,220mm(42"×48")	

Remarks: Other sheet size and thickness could be available upon request.